


WEST COAST FILTERS INC.

Design, Manufacture & Distribution of Water Purification Equipment

Filter Gravel 1/4" X 1/8"



Typical Product Analysis:

USE Sieve	% Retained	% Cumulative	% Passing
3/8"	0.0	0.0	100.0
1/4"	3.4	3.4	96.6
4 Mesh	34.7	38.1	61.9
6 Mesh	56.8	94.9	5.1
1/8"	2.0	96.9	3.1
Pan	3.1	100.0	0.0
E.S.	3.5		
U.C.	1.30		

Technical Data:

Acid Solubility	<1%	% Fe ₂ O ₃	0.083
Specific Gravity	2.64	% Al ₂ O ₃	0.134
Porosity	40	% MgO	0.010
Moh Hardness	7.0	% Na ₂ O	0.008
% Fractured Faces	N/A	% Cr ₂ O ₃	0.000
Flat & Elongates	N/A	%CaO	0.012
Fusion Point	3,150°	% K ₂ O	0.031
Roundness	0.8 ***	% TiO ₂	0.021
Sphericity	0.8 ***	% LOL	0.141
Bulk Density	100# / ft. ³	% SiO ₂	99.555

*** As determined by an independent lab using the methods outlined in "Elements of Water Supply and Wastewater Disposal", 2nd edition, John Wiley & sons, Inc.