


# WEST COAST FILTERS INC.

Design, Manufacture & Distribution of Water Purification Equipment

## Filter Gravel 1 1/2" X 3/4"



Typical Product Analysis:

USE Sieve	% Retained	% Cumulative	% Passing
1 3/4"	0.0	0.0	100.0
1 1/2"	4.4	4.4	95.6
1 1/4"	22.4	26.8	73.2
1"	46.3	73.1	26.9
3/4"	23.2	96.3	3.7
Pan	3.7	100.0	0.0

Technical Data:

Acid Solubility	<1%	% Fe <sub>2</sub> O <sub>3</sub>	0.083
Specific Gravity	2.64	% Al <sub>2</sub> O <sub>3</sub>	0.134
Porosity	40	% MgO	0.010
Moh Hardness	7.0	% Na <sub>2</sub> O	0.008
% Fractured Faces	N/A	% Cr <sub>2</sub> O <sub>3</sub>	0.000
Fusion Point	3,150°	%CaO	0.012
Roundness	0.8 ***	% K <sub>2</sub> O	0.031
Sphericity	0.8 ***	% TiO <sub>2</sub>	0.021
Bulk Density	100# / ft. <sup>3</sup>	% LOL	0.141
		% SiO <sub>2</sub>	99.555

\*\*\* As determined by an independant lab using the methods outlined in "Elements of Water Supply and Wastewater Disposal", 2nd edition, John Wiley & sons, Inc.